

■ **Classic Impression Grade I**
Faux Leather



**WORKING
FOR
YOU**




KHAKI
1283



WINE SAP
1280



SADDLE
1296



OAK
1281




CHESTNUT
1274



CLARET
1293



DUNE
1272




BUTTER
1282



MOCHA
1286



BLACK ROSE
1278



TRUFFLE
1275




KHAKI
1283



EVERGREEN
1291



BLUEBERRY
1276



EGGSHELL
1295








STORM
1279



BLACK
1294

■ Specification Information

Description	Classic Impression
Grade	I
Content	100% Nylon Fiber Matrix
Repeat	None
Width	54"
Performance	
 Abrasion	Passes ASTM D4157-82 100,000 double rubs Wyzenbeek method. Abrasion resistance is the surface wear of a fabric caused by rubbing and contact with another fabric.
 Physical Properties	Trap Tear Strength, 35 lbs. x 25 lbs. (ASTM D-1117-80). Grab Tensile Strength, 130 lbs. x 90 lbs. (ASTM D-5034-90). Seam Strength, 100 lbs. x 80 lbs. (ASTM D-1683-90A).
 Colorfastness to Wet and Dry Crocking	Passes AATCC 8-1988 Dry Crocking, Grade 5. Wet Crocking, Grade 5. Crocking is the transfer of dye from the surface of a dyed or printed fabric onto another surface by rubbing.
 Colorfastness to Light	Fadeometer Test (AATCC 16A-90, 100 hours). Colorfastness to light refers to a material's degree of resistance to the fading effect of light.
 Flame Resistance	Passes California Technical Bulletin #117 Section E – Class I. Flame resistance is the measurement of a fabric's performance when it is exposed to specific sources of ignition.

Colors may vary slightly between dye lots.

KI and Working For You
are registered trademarks of
Krueger International, Inc.

© 2007 KI Litho in USA KI-32431/HC/EWB/108

